

# DuPont™ Teflon®

## Industrial Coatings

### **Teflon® S Coatings** **954-201, 954-203 and 954-407**

#### **Description**

These *Teflon*® single-coat, nonstick finishes are formulated primarily for chemical and corrosion resistance, with low temperature curing requirements.

#### **FDA Status**

The *Teflon*® S 954-200 system does not comply with FDA regulations governing components of coatings for direct food contact.

**Table 1**  
**Typical Properties**

Product Code	954-201	954-203	954-407
Color	Green	Black	Flat Black
Weight Solids, %	39.4	33.3	36.6
Volume Solids, %	26.1	24.1	25.3
Density, lb/gal	8.8	8.2	8.4
(kg/L)	1.06	0.99	1.00
Coverage, ft <sup>2</sup> /gal*	418	387	406
(m <sup>2</sup> /L)*	10.4	9.6	10.1
Viscosity, (cP)	100–650	150–450	200–550
Maximum Use Temperature, °C (°F)	Continuous: 150 (300) Intermittent: 165 (325)		

**Note:** These figures are averages and may vary.

\* Theoretical coverage at 25 µm (1 mil) assuming 100% spray efficiency.

#### **Application**

Roll or agitate with a propeller-type mixer until contents are homogeneous.

Strain through 150-mesh wire screen or cheese cloth.

Use conventional industrial spray equipment.

Manual or Automatic Spray: No reduction required. If lower viscosity is desired, reduce with MEK or toluene.

See “Applying *Teflon*® Coatings” fact sheet.

#### **Surface Preparation**

Apply over clean, roughened surface. Any residual oil on the surface will affect the color of the cured film and will adversely affect adhesion.

Corrosion resistance is improved by applying over phosphated steel.

#### **Film Thickness**

13–25 µm (0.5–1.0 mil) DFT

Products are recoatable and may be applied in multiple coats to a maximum DFT of 30 µm (1.2 mil). No special intercoat surface preparation is required.

#### **Cure**

All temperatures refer to metal temperature.

Air or force dry 1-5 min. to drive off volatile substances and excess water.

Bake: 10 min. at 163°C (325°F) *or*  
5 min. at 177°C (350°F)

#### **Storage and Stability**

Shelf life is at least 18 months when stored at normal room temperature, 18°–24°C (65°–75°F).

Material may be exposed briefly to temperatures outside the suggested temperature range without harm. In such cases, check product and properties before extensive use.

## Safety

Follow normal industrial safety practices for handling and applying *Teflon*<sup>®</sup> products. Industrial experience has clearly shown *Teflon*<sup>®</sup> materials can be processed and used at elevated temperatures without hazard providing adequate ventilation is used. Ventilation should be available at baking temperatures of 275°C (525°F) and above. Before using *Teflon*<sup>®</sup>, read the Material Safety Data Sheet (MSDS) and the detailed information in the "Guide to the Safe Handling of Fluoropolymer Resins," latest edition, published by the Fluoropolymers Division of The Society of the Plastics Industry.

When grit-blasting *Teflon*<sup>®</sup> finishes off aluminum or magnesium surfaces, the possibility of explosion exists if the fines are allowed to heat up. Good house-keeping practices, keeping the residue wet, and keeping the ventilation and dust collection systems in good working order reduces this risk.

---

### For more information on *Teflon*<sup>®</sup> coatings:

DuPont  
*Teflon*<sup>®</sup> Nonstick & Industrial Coatings  
Chestnut Run Plaza  
P.O. Box 80702  
Wilmington, DE 19880-0702

**(800) 441-7515**  
**Fax: (302) 366-8602**

**[www.dupont.com/teflon/coatings](http://www.dupont.com/teflon/coatings)**

---

### Europe

DuPont de Nemours (Belgium)  
A. Spinostraat 6  
B-2800 Mechelen  
Belgium  
Tel.: 33-15-441188  
Fax: 33-15-441160

### Pacific

DuPont Australia, Ltd.  
254 Canterbury Road  
Bayswater, Victoria 3153  
Australia  
Tel.: 61-3-9721-5617  
Fax: 61-3-9721-5690

### Japan

DuPont K. K. (*Teflon*<sup>®</sup> Finishes)  
4th Floor, Chiyoda Honsha Building  
5-18 Sarugaku-cho, 1-chome  
Chiyoda-ku, Tokyo, 101 Japan  
Tel.: 81-3-5281-5888  
Fax: 81-3-5281-5899

---

### Asia

DuPont China, Ltd.  
26/F., Tower 6, The Gateway  
9 Canton Road, Tsimshatsui  
Kowloon, Hong Kong  
Tel.: 852-2734-5459  
Fax: 852-2368-3512

DuPont Korea  
4/5th Floor Asia Tower  
#726 Yeoksam-dong, Kangnam-ku  
Seoul, Korea  
Tel.: 82-2-2222-5385  
Fax: 82-2-2222-5478

---

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

**CAUTION:** Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102.

