

DuPont™ Teflon®

Industrial Coatings

Teflon® Primer 855-300

Description

Teflon® 855-300 is a water-based primer and is not recommended as a one coat. Refer to **Table 1** for physical property data.

FDA Status

Teflon® 855-300 does not comply with FDA regulations in 21 CFR governing components of coatings for direct food contact.

Table 1
Typical Properties

855-300	
Color	Blue
Weight Solids, %	23.8
Volume Solids, %	13.4
Density, lb/gal	9.5
kg/L	1.13
Coverage, ft ² /gal*	215
m ² /L	5.4
Viscosity, cP	150–400
Maximum Use Temperature	**

Note: These figures are averages and may vary.

*Theoretical coverage at 1 mil (25 µm) assuming 100% spray efficiency.

** Dependent upon Topcoat. Refer to Fact Sheet on Topcoat.

Substrates

Teflon® 855-300 primer can be used on carbon steel, stainless steel, and aluminum substrates. Substrates must be free of contamination and thoroughly cleaned. To obtain maximum adhesion, grit-blasting is recommended to a profile of 4–8 µm (0.2–0.3 mil). The primer should be applied immediately after blasting on carbon steel to minimize flash rusting. Refer to the Fact Sheet on Application.

Topcoats

Teflon® 855-300 is recommended for liquid topcoats 855-401, 855-403, and 855-500.

Application

1. Bring material to room temperature.
2. Mix thoroughly and filter the material through a 100-mesh stainless steel screen (0.146 mm openings).
3. The primer is supplied ready to spray. Use conventional industrial spray equipment.
4. Apply at dry film thickness of 5–8 µm (0.2–0.3 mil). On carbon steel, cover blast profile for best results.

Bake

As primer for liquid topcoats:

1. Primer should be applied and dried immediately. Force dry at 220°C (430°F) for 10 min.
2. Apply midcoat and/or topcoat and bake as recommended by the Fact Sheet on Topcoat. No problems are encountered if the *primer* is sprayed onto warm (40–60°C [100–140°F]) metal.

Note: First bake should be 500°F (260°C) for 2 minutes and then follow final bake requirement of topcoat.

Storage and Stability

Teflon® 855-300 has a shelf life of at least 12 months when stored at normal room temperature, 18–24°C (65–75°F).

Safety

Follow normal industrial safety practices for handling and applying *Teflon*® products. Industrial experience has clearly shown *Teflon*® materials can be processed and used at elevated temperatures without hazard providing adequate ventilation is used. Ventilation should be available at baking

temperatures of 275°C (525°F) and above. Before using *Teflon*®, read the Material Safety Data Sheet (MSDS) and the detailed information in the “Guide to the Safe Handling of Fluoropolymer Resins,” latest edition, published by the Fluoropolymers Division of The Society of the Plastics Industry.

When grit-blasting *Teflon*® finishes off aluminum or magnesium surfaces, the possibility of explosion exists if the fines are allowed to heat up. Good housekeeping practices, keeping the residue wet, and keeping the ventilation and dust collection systems in good working order reduces this risk.

For more information on Teflon® coatings:

DuPont
Teflon® Industrial Coatings
Chestnut Run Plaza
P.O. Box 80702
Wilmington, DE 19880-0702

(800) 441-7515
Fax: (302) 366-8602
www.dupont.com/teflon/coatings

Europe

DuPont de Nemours (Belgium)
A. Spinostraat 6
B-2800 Mechelen
Belgium
Tel.: 33-15-441188
Fax: 33-15-441160

Pacific

DuPont Australia, Ltd.
254 Canterbury Road
Bayswater, Victoria 3153
Australia
Tel.: 61-3-9721-5617
Fax: 61-3-9721-5690

Japan

DuPont K. K. (*Teflon*® Finishes)
4th Floor, Chiyoda Honsha Building
5-18 Sarugaku-cho, 1-chome
Chiyoda-ku, Tokyo, 101 Japan
Tel.: 81-3-5281-5888
Fax: 81-3-5281-5899

Asia

DuPont China, Ltd.
26/F., Tower 6, The Gateway
9 Canton Road, Tsimshatsui
Kowloon, Hong Kong
Tel.: 852-2734-5459
Fax: 852-2368-3512

DuPont Korea
4/5th Floor Asia Tower
#726 Yeoksam-dong, Kangnam-ku
Seoul, Korea
Tel.: 82-2-2222-5385
Fax: 82-2-2222-5478

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see “DuPont Medical Caution Statement,” H-50102.

© 2004. E. I. du PONT de NEMOURS AND COMPANY.
ALL RIGHTS RESERVED.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING, OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.



The miracles of science™