

DuPont™ Teflon®

Nonstick & Industrial Coatings

856-200, 856-204, and 856-211 DuPont™ Teflon® 856-Line FEP Topcoats

Description

Teflon® FEP topcoats provide nonstick, chemical and corrosion resistance. Because FEP can melt-flow to form nonporous film, it is a natural choice for release applications with low abrasion such as molds and bakeware.

The 856-line of Teflon® topcoats must be used with a Teflon® industrial coatings primer. Examples:

FDA Conforming Primers	Not FDA Conforming Primers
858-100	851-204
959-200 series	850-300 series
959-405	958-200 series

FDA Status

The 856-200 Teflon® topcoat complies with FDA regulations in 21CFR governing components of coatings for direct food contact when applied according to fact sheet instructions. Primers must also comply for the system to be FDA conforming. **Note:** 856-204 and 856-211 Teflon® topcoats do not comply with FDA regulations in 21CFR.

Table 1
Typical Properties

	856-200	856-204	856-211
Color	Clear	Green	Gray
% Weight Solids	44.9	44.1	46.3
% Volume Solids	26.4	24.4	24.3
Coverage, ft ² /gal* (m ² /l)*	423 10.4	391 9.7	453 11.1
Viscosity, cP	20–400	50–300	20–300
Maximum use temperature, °C (°F)		204 (400)	

* Theoretical coverage at 25 µm (1 mil) assuming 100% spray efficiency.

These figures are averages and may vary.

Application

Bring coating to room temperature. Roll or agitate gently but thoroughly until contents are homogeneous. Do not use a lightening mixer or similar type of mixer. Strain through 100-mesh stainless steel screen. See “Applying Teflon® Coatings” fact sheet.

Surface Preparation

Apply primer over clean and roughened surface and apply as directed on primer fact sheet. Bake or force dry per directions in appropriate primer fact sheet.

Film Thickness

Apply 856-2XX coatings at a total DFT of 15-25 µm (0.6-1.0 mil) with a primer thickness of approximately 7 µm (0.3 mil). Flash dry to prevent popping or cracking during the bake.

Bake

All temperatures refer to metal temperature. For end uses where low porosity is essential, multiple topcoats are required using the higher temperature bakes.

Primer

See specific fact sheets for primers.

Single top coat

The first topcoat must be sufficiently baked to cure the primer. For example:

Bake	If Using Primer
5 min. at 400°C (750°F) or 10 min. at 370°C (700°F)	850-3XX line; 851-204; 858-100
60 min. at 300°C (575°F) or 5 min. at 370°C (700°F)*	958-2XX line; 959-line

Multiple top coats

Apply another 10–15 µm (0.4–0.6 mil) of 856-line FEP topcoat. Bake 30 min. at 330–343°C (625–650°F). Repeat for all subsequent coats until desired film build up to 125 µm (5 mil) is reached.

The DuPont Oval Logo, DuPont™, and Teflon® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company.

Use of DuPont trademarks subject to License Agreement and qualification.

Repair

Re-baking above 300°C (575°F) may cause sufficient flow to eliminate the damaged area, otherwise: Roughen surface thoroughly with 400–600 grit sandpaper. Clean surface thoroughly with xylene or alcohol. Allow to dry.

Apply 7–15 µm (0.3–0.6 mil) of 856-line topcoat. Air dry, then bake 15–30 min. at 300°C (575°F).

Storage and Stability

Do not allow product to freeze. Material may be exposed briefly to temperatures outside the suggested temperature range without harm. In such cases, check product and properties before extensive use.

856-line: At normal room temperature, 18–24°C (65–75°F), these products have a shelf life of 18 months.

Safety

Follow normal industrial safety practices for handling and applying *Teflon*® products. Industrial experience has clearly shown *Teflon*® materials can be processed and used at elevated temperatures without hazard providing adequate ventilation is used. Ventilation should be available at baking temperatures of 275°C (525°F) and above. Before using *Teflon*®, read the Material Safety Data Sheet (MSDS) and the detailed information in the “Guide to the Safe Handling of Fluoropolymer Resins,” latest edition, published by the Fluoropolymers Division of The Society of the Plastics Industry.

When grit-blasting *Teflon*® finishes off aluminum or magnesium surfaces, the possibility of explosion exists if the fines are allowed to heat up. Good house-keeping practices, keeping the residue wet, and keeping the ventilation and dust collection systems in good working order reduces this risk.

For more information on Teflon® coatings:

DuPont
Teflon® Nonstick & Industrial Coatings
Chestnut Run Plaza
P.O. Box 80702
Wilmington, DE 19880-0702

(800) 441-7515
Fax: (302) 366-8602
www.dupont.com/teflon/coatings

Europe

DuPont de Nemours (Belgium)
A. Spinoystraat 6
B-2800 Mechelen
Belgium
Tel.: 33-15-441188
Fax: 33-15-441160

Pacific

DuPont Australia, Ltd.
254 Canterbury Road
Bayswater, Victoria 3153
Australia
Tel.: 61-3-9721-5617
Fax: 61-3-9721-5690

Japan

DuPont K. K. (*Teflon*® Finishes)
4th Floor, Chiyoda Honsha Building
5-18 Sarugaku-cho, 1-chome
Chiyoda-ku, Tokyo, 101 Japan
Tel.: 81-3-5281-5888
Fax: 81-3-5281-5899

Asia

DuPont China, Ltd.
26/F., Tower 6, The Gateway
9 Canton Road, Tsimshatsui
Kowloon, Hong Kong
Tel.: 852-2734-5459
Fax: 852-2368-3512

DuPont Korea
4/5th Floor Asia Tower
#726 Yeoksam-dong, Kangnam-ku
Seoul, Korea
Tel.: 82-2-2222-5385
Fax: 82-2-2222-5478

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see “DuPont Medical Caution Statement,” H-50102.

